

PRODUCT DESCRIPTION

PlekoSkim Crack Filler is a high quality, polymer modified, cementitious crack filler for surface preparation and repair of cracks up to 4mm. It is composed of white hydraulic binders, selected fine aggregates, bonding agents, and special chemical additives. It is easy to use by just adding water, improving on-site quality control.

USES

As a filler for cracks up to 4mm and to smooth surface and level minor irregularities on plastered wall and concrete; for interior and exterior use, in wet and dry areas.

APPROVED SUBSTRATES

PlekoSkim Crack Filler can be used directly onto plastered wall, gypsum boards, cement boards, concrete... in dry or wet areas.

PACKAGING

20 or 50 kg in multiply paper bag or 1.5Ton in jumbo bag

COVERAGE

0.8-1.1 Kg/m²/mm depending on surface condition and application method.

Recommended thickness between 0.5-3 mm

Manufacturer does not warrant square meter coverage, which can vary greatly according to application techniques.

PROPERTIES

- **Easy to use**
- **Low Shrinkage**
- **Smooth Surface**
- **Superior Bonding Strength**
- **Interior & Exterior Use**
- **Factory Controlled Quality**

TECHNICAL DATA

Appearance	Free-flowing whitish powder
Bulk Density (Kg/L ± 0.5)	1.12
Water Demand (%)	34-39
Setting Time (hrs)	6-8
Tensile Bond Strength* (N/mm ²)	>0.65

*after 28 days

INSTALLATION

SUBSTRATE PREPARATION

Surface must be sound, clean, dry, free of bond-inhibiting materials such as paint, grease, oil, efflorescence, form release agents and curing compounds. It should have been sufficiently cured in a way that any shrinkage has already occurred. Moisten slightly the substrate with clean water prior to application. Surface should appear damp with no water running.

MIXING

Use a clean container free of all foreign substances for preparing and mixing material. Use a heavy duty electric drill and mixing paddle. Pour the water in contained and add powder in small increments while mixing thoroughly to achieve lump-free consistency. Avoid working excessively to prevent air entrapment. Let mixture set for 5 minutes and re-temper. Small amount of clean water may be added if necessary to improve workability, but keep within recommended range; excess water may result in cracks and strength reduction. Do not add water once the mixed mortar starts to harden. Mixture should be used within 1.5 hrs from mixing.

For additional water resistance up to 1 liter of polymer from the PlekoBond product line can be added.



PlekoSkim Crack Filler

APPLICATION

Firmly press Pleko PlekoSkim Crack Filler in crack using putty knife. For wide and deep cracks apply in 2 coats. Once the first coat sets wet the surface and apply second coat.

CURING

Pleko PlekoSkim Crack Filler doesn't require curing unless in extreme conditions, if so spray clean potable water.

LIMITATIONS

Apply only to unfrozen surfaces above 4 °C (40°F). Maintain minimum 4 °C (40°F) ambient temperature for 24 hours after application. Protect from direct sunlight, wind and rain during application

Do not mix with any additive or product unless recommended by Pleko.

Pleko bears no responsibility for the defects due to the improper or non-recommended use of the product.

CLEANING

While still fresh, soluble in water. Clean all equipment with water immediately after use. After hardening, tools should be cleaned mechanically.

STORAGE

Store in cool, dry, well-ventilated area, protected from freeze, heat and direct sunlight and at a temperature between 4°C (40°F) and 38°C (100°F), in tightly sealed original container off the ground. Storage time must not exceed one year.

HEALTH AND SAFETY

Avoid contact with eyes and skin. Prevent inhalation of dust.

The product contains cement powders which, when mixed with water, release alkalis that could be harmful to the skin. It is preferable that the application be done in a ventilated area, and to wear protective gear for hands, eyes and respiratory system and to avoid breathing of the dust. Splashes on the skin should be washed away by cleaning with soap and water. In case of contact with eyes, wash thoroughly with clean water. If swallowed, do not induce vomiting, in both cases seek medical attention.

The product is non-flammable

Attention

This product is intended for use by qualified professional contractors, as a component of a larger construction system and specification. It should be installed in accordance with given instructions and specifications. Information listed above reflects the criteria for our internal quality test and practical experience. Results depend on listed instructions and consumer skills and are therefore out of our responsibility whether expressed or implied. All values are valid for the product when dispatched from the plant. Technical data are generated under laboratory conditions, some variations are expected due to weather, site, and application conditions which are beyond the control of the manufacturer. We reserve the right to change any given specification without notice.